

SILICA ABRASIVE

October, 04 Page 1 of 2

PRODUCT

TARGET® Silica Abrasives are high quality, close graded silica sands which are produced at our Morinville, Alberta, plant in ten size grades. Typical gradations are presented in the following tables.

USES

TARGET Silica Abrasives are suitable for all applications requiring a high quality, clean, well graded sand. Typical uses include:

- Sandblasting of steel, concrete or wood in preparation for surface coating or repair
- Sandblasting of concrete or wood to obtain architectural effects
- Aggregate for cementitious or polymer mortars, grouts and concretes
- Foundry mold sand
- Traction sand

PHYSICAL PROPERTIES

Colour	Tan
Grain Shape	Sub-rounded
Bulk Density	92 - 95 lb/ft ³ (1474 - 1522 kg/m ³)
Hardness, Moh	6.5 - 7
Specific Gravity	2.65
Moisture Content	<0.1 % weight

PACKAGING

TARGET Silica Abrasives are available in 25 kg (55 lb) and 40 kg (88 lb) multi-wall paper bags, 1680 kg (3700 lb) bulk bags, or as bulk deliveries in dump trucks or pneumatic tankers.

TYPICAL CHEMICAL ANALYSIS

Chemical Oxide	% weight	Typical Value
Silica	SiO ₂	93.2 - 93.6
Alumina	Al ₂ O ₃	3.6 - 4.6
Iron	Fe ₂ O ₃	0.30 - 0.35
Calcium	CaO	0.25 - 0.65
Magnesium	MgO	0.08 - 0.15
Sodium	Na ₂ O	0.75 - 0.85
Titanium	TiO ₂	0.1 maximum
Loss on Ignition		0.3 maximum

Product performance is affected by many factors, including storage, method and conditions of application and use. User testing is ESSENTIAL to determine suitability of product for intended method of application and use. Target's SOLE WARRANTY is that the product has been manufactured to specifications. No oral or written information or advice shall increase this warranty or create new warranties. Target's SOLE LIABILITY is to replace product proved defective. In no event shall Target be liable for any consequential, indirect or other damages whether arising from negligence or otherwise.

TARGET is a registered trade-mark of Tegrat Holdings Ltd. Target Products Ltd. is an authorized licensee.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D



SILICA ABRASIVE

October, 04 Page 2 of 2

TYPICAL SIEVE ANALYSES

SIEVE SIZE		CUMULATIVE PERCENT PASSING								
U.S.	mm	16-30	12-40	20-40	12-50	12-50 Special	30-50	40-70	50-100	60-140
4	4.75									
8	2.36									
10	2.00	100	100		100	100				
16	1.18	95+	90-95	100	88-98	90-98				
20	0.85	15-35	65-80	90+	65-85	80-90	100	100		
30	0.60	0-7	20-45	35-55	25-45	45-65	80+	98+	100	100
40	0.425	0-2	10-25	10-20	10-25	20-30	30-45	60-80	96+	96+
50	0.300		0-2	0-3	1-5	2-10	0-10	15-30	15-35	80-90
70	0.212					0-2	0-2	1-3	1-8	65-80
80	0.180							0-1	0-2	50-70
100	0.150								0-1	35-45
140	0.106									10-20
Profile, mils			3.0-3.5		2.8-3.5		2.3-2.8		1.8-2.3	<1.8

SIEVE SIZE		INDIVIDUAL PERCENT RETAINED								
U.S.	mm	16-30	12-40	20-40	12-50	12-50 Special	30-50	40-70	50-100	60-140
4	4.75									
8	2.36									
10	2.00									
16	1.18	0-5	5-10		2-12	2-10				
20	0.85	40-65	10-25	0-10	5-25	5-15				
30	0.60	20-40	35-50	50-65	25-45	15-40	5-25	0-2		
40	0.425	5-15	20-30	20-40	15-35	20-40	40-60	20-40	0-4	0-4
50	0.300		5-15	5-15	10-20	15-30	20-35	45-65	50-90	5-15
70	0.212					2.8	0-10	15-25	10-30	10-20
80	0.180								1-5	10-20
100	0.150								0-2	15-25
140	0.106									20-35
Pan		0-1	0-2	0-2	0-3	0-2	0-2	1-3	0-1	5-15

TARGET PRODUCTS LTD



Product performance is affected by many factors, including storage, method and conditions of application and use. User testing is ESSENTIAL to determine suitability of product for intended method of application and use. Target's SOLE WARRANTY is that the product has been manufactured to specifications. No oral or written information or advice shall increase this warranty or create new warranties. Target's SOLE LIABILITY is to replace product proved defective. In no event shall Target be liable for any consequential, indirect or other damages whether arising from negligence or otherwise.

TARGET is a registered trade-mark of Tegrat Holdings Ltd. Target Products Ltd. is an authorized licensee.