

1117 GROUT

(Silica Fume ANCHOR BOLT GROUT)

August, 2024 Page 1 of 3

PRODUCT

TARGET® Silica Fume Anchor Bolt Grout consists of accurately weighed Portland cement, silica fume and special chemical admixtures. The product is designed for use as a flowable grout. In working temperature ranges of 5 °C to 35 °C (41 °F to 95 °F), the grout will have a slight expansion prior to final set. The grout contains no chlorides or other admixtures that could aggravate corrosion of embedded steel and meets all the requirements as set forth in ASTM C1107 specification for pre-hardened and post hardened expansion.



USES

TARGET Silica Fume Anchor Bolt Grout is primarily designed for uses where a premium quality high flow grout that inhibits washout by water and has a very low permeability is required and a higher early strength is desired.

Applications include:


- Soil tie back anchor grouting
- Grouting of fissures and cracks in rocks
- Anchor bolt grouting
- Any area where there is a possibility of running water washing out the cement component in conventional grouts before they achieve final set
- Situations where a higher early strength is required

TYPICAL PROPERTIES OF TARGET 1117 SILICA FUME ANCHOR BOLT GROUT at fluid consistency

(Corps of Engineers CRD-C62I and ASTM Standard C1107 test procedures)

PROPERTY	TYPICAL VALUE	
FLOW (ASTM C 939) Water used, litres/30 kg (66 lb) bag	20 - 30 seconds Max. 10.5 litres (11 US liq qt)	
EXPANSION, BEFORE SETTING. (ASTM C 940) % volume unconfined	1 – 3 %	
SETTING TIME hours at 20 °C (68 °F)	Initial	6
	Final	8
COMPRESSIVE STRENGTH, ASTM C109 - MPa (lb/in ²)	20 °C (68 °F) ± 2 °C 50% RH	8 °C (46 °F)
at 18 hours	17.9 MPa (2600 psi)	N/A
at 24 hours	28.8 MPa (4,180 psi)	7.2 MPa (1,050 psi)
at 7 days	75.8 MPa (11,000 psi)	67.5 MPa (9,800 psi)
at 28 days	82.7 MPa (12,000 psi)	68.9 MPa (10000 psi)
SEGREGATION	Nil	

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2024 Quikrete International, Inc.



1117 GROUT

(Silica Fume ANCHOR BOLT GROUT)

August, 2024 Page 2 of 3

PROCEDURES

WEAR IMPERVIOUS GLOVES, such as nitrile.

1. The grout must be mixed in a high-speed shear mixer such as a Jiffler mixer or equivalent.
2. Add the grout to clean water and mix to a uniform consistency. Water temperature should be 10 °C to 18 °C (50 °F to 65 °F).
3. The grout can be mixed to plastic, flowable or fluid consistencies, depending on the job application. The water content of the grout should be kept as low as possible, and not exceed 10.5 litres (11 US liq qt) of water per 30 kg (66 lb) bag of TARGET Silica Fume Anchor Bolt Grout.
4. Mix the grout continuously for at least 5 minutes before placing. If possible, the grout should be mixed continuously until placing is completed, but if this is not practical, a brief remixing for 1 minute prior to pumping or placement is adequate to overcome the effect of "thixotropic set" caused by the silica fume.
5. Place, using a grout pump or other established grouting procedures. The placement method will depend on the application and grout consistency.
6. In order to obtain full expansion of the grout in place, limit batch sizes to the amount of grout placement that can be completed within 1 hour.

CAUTION

- The grout is not recommended for heavy duty precision grouting of machinery base plates or crane rails unless adequate neoprene pads or equivalent vibration and energy absorbing materials are included in the design detail.
- The grout performs best when fully restrained or confined on all surfaces.
- Pours with least dimensions (thickness) in excess of 50 mm (2 inches) are not recommended.
- Ambient temperatures should be between 10 °C (50 °F) and 30 °C (86 °F). Cooler temperatures will retard the rate of strength gain, especially in flowable or fluid mixes. Foundation and bed plate temperatures should be kept above 5 °C (41 °F) and below 35 °C (95 °F) for at least 72 hours after grouting.

APPROXIMATE YIELD

per 30 kg (66 lb) bag at fluid consistency

bags/m ³	50
bags/yd ³	38
litres/bag	20.1
ft ³ /bag	0.71

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2024 Quikrete International, Inc.



T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

1117 GROUT

(Silica Fume ANCHOR BOLT GROUT)

August, 2024 Page 3 of 3

SPECIFICATION GUIDE

Grout shall be TARGET Silica Fume Anchor Bolt Grout or approved equivalent product meeting the requirements of US Corps of Engineers Specification CRD-C621 and ASTM Standard Specification C1107 for Non-Shrink Grout. The grout shall develop a compressive strength of not less than 82.7 MPa (12,000 lb/in²) after 28 days (20 °C) when mixed and cured in accordance with the manufacturer's directions.

PACKAGING

TARGET Silica Fume Anchor Bolt Grout - Stock Code 9991117 - is available in 30 kg (66 lb) bag 42 bags /pallet.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2024 Quikrete International, Inc.