DRYMIX BRAND TECHTURE® 200 | 300

June 2019 Page 1 of 3

PRODUCT

DRYMIX TECHTURE[®] Finish Coat Stucco is designed and manufactured to be the final coat in a three coat Stucco Application. **DRYMIX TECHTURE** Finish Coat Stucco was designed for use with DRYMIX Brand Premium Colour Pigments.

FEATURES

DRYMIX TECHTURE Finish Coat Stucco

- Provides consistency in quality of mix.
- Provides consistent results with the addition of colour.
- Provides for ease of application with consistent results.

MIXING INSTRUCTIONS

ALWAYS USE AN APPROVED DUST MASK WHEN LOADING MIXER WITH DRY MATERIALS.

DRYMIX TECHTURE Bases' are complete except for <u>measured</u> amounts of clean potable water and desired colour pigment.

Base 200 (T200) light grey mixture,

Base 300 (T300) darker grey mixture,

Do not add any other ingredients.

If a special blend is required for your purpose, contact TARGET.

Mixing

For best results keep the mix wet.

Do not let the mix become dry or tight! Allow the mix to have as much water as it requires.

With the mixer running,

- Add 30 litres of clean potable water.
- Add all appropriate colour packs.
- <u>All DRYMIX Colour is added at the rate of one pack for two 40 kg bags of the</u> correct **DRYMIX TECHTURE** Base.
- Add 3 bags of **DRYMIX TECHTURE** (120 kg)
- Add 25 litres of clean potable water.
- Add 3 bags of DRYMIX TECHTURE (120 kg)
- Add additional water to desired consistency.

Approximate water requirement, 10 litres per 40 kg bag.

DRYMIX BRAND TECHTURE® 200 | 300

June 2019 Page 2 of 3

Mixing continued

When all material is in mixer, mix until no dry parts is evident, about 2 minutes. At this point the mix should be slightly wetter or of higher flow than desired for spreading.

- Stop mixer for a minimum of 10 minutes.
 - This will allow the lime to fatten and all other ingredients to absorb water and wet out. Mix will thicken. (Longer is better...lime may require up to 30 minutes to achieve optimum plasticity.)
- Restart mixer for 1 minute before adding additional water. Add additional water carefully.
- Mix for 1 to 2 more minutes. Do not run mixer continuously

Excessive mixing will entrain excessive air and reduce the strength.

Cover mixer during hot weather. Use mix within 1.25 hour from final mixing.

COVERAGE

Each 40 kg (88 lb) bag of **DRYMIX TECHTURE** will cover approximately $6.5 - 7.5 \text{ m}^2$ (70-80 ft²) at 3 mm (1/₈ inch) thickness.

SIZE

DRYMIX TECHTURE comes in 40 kg (88 lb) bags packaged 40 bags per pallet.

STORAGE

Store in a dry place. Keep out of reach of children.

CAUTION

ALWAYS USE AN APPROVED DUST MASK WHEN LOADING MIXER WITH DRY MATERIALS.

When mixed with water, the cement in this product forms a caustic solution of calcium hydroxide. Avoid contact with eyes. Avoid ingestion or inhalation. Wear appropriate clothing when working with **DRYMIX TECHTURE** and avoid contact with skin, or with wet clothing.

First Aid Treatment: If splashed in eyes or on skin, flush thoroughly with water. Obtain Medical advice if irritation persists.



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA. TECHTURE[®] is a trademark of Drymix Systems, Inc., Target Products Ltd. is an authorized licensee. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.

DRYMIX BRAND TECHTURE® 200 | 300

June 2019 Page 3 of 3

COVERAGE

Each 40 kg (88 lb) bag of DRYMIX Techture will cover approximately 6.5-7.5 m² (70-80 ft²) at 3 mm ($\frac{1}{8}$ inch) thickness.

SIZE

DRYMIX Techture comes in 40 kg (88 lb) bags packaged 40 bags per pallet.

STORAGE

Store in a dry place. Keep out of reach of children.

CAUTION *ALWAYS USE AN APPROVED DUST MASK WHEN LOADING MIXER WITH DRY MATERIALS.*

When mixed with water, the cement in this product forms a caustic solution of calcium hydroxide. Avoid contact with eyes. Avoid ingestion or inhalation. Wear appropriate clothing when working with DRYMIX Techture and avoid contact with skin, or with wet clothing.

First Aid Treatment: If splashed in eyes or on skin, flush thoroughly with water. Obtain Medical advice if irritation persists.



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA. TECHTURE[®] is a trademark of Drymix Systems, Inc., Target Products Ltd. is an authorized licensee. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.