

CEMENT/SILICA FUME SLURRY GROUT

April, 2025 Page 1 of 1

PRODUCT and USES

TARGET® Cement/Silica Fume Slurry Grout consists of accurately weighed and blended Portland cement, silica fume and graded sand combined in the 46/4/50 parts by weight proportions specified by many authorities for improving the adhesion of overlay or repair concrete to bridge decks and other concrete structures. Target Cement/Silica Fume Slurry Grout can also be mixed with Target's Polymer Bonding Agent for added bond strength.

ADVANTAGES

1. Reduced materials inventory – only one material is needed, instead of three.
2. Accurate pre-blending of the ingredients of TARGET Cement/Silica Fume Slurry Grout in the required proportions eliminates the variability that inevitably occurs when site batching is used to prepare slurry grouts.

PROCEDURES

Follow the procedure outlined in CSA Standard A23.1, Section 23.4, Bonded Toppings. After surface preparation has been completed in accordance with the project requirements, the steps required for applying the bonding slurry include:

1. Before applying the bonding slurry grout, continuously soak the repair area for a minimum of 3 hours with potable water.
2. Just before concrete placing commences, remove excess water, using oil-free compressed air if necessary. Allow the surface to become dry, as indicated by a change from dark to light colour, just before applying the slurry and commencing concrete placing.
3. Mix TARGET Cement/Silica Fume Slurry Grout with potable water to an appropriate consistency for the work. *If utilizing Target Polymer Bonding Agent; add two litres prior to any water being added. The consistency should be such that the mixture can be applied with a stiff brush or broom to give a uniform, thin coating over the concrete surface with no tendency to run or pond in low spots.
4. Apply the slurry grout immediately before placing the repair concrete. Do not allow the grout to dry or set before placing concrete.
5. Mixed grout that has not been applied to the surface should be remixed at frequent intervals to prevent segregation. Discard any grout that has not been applied within 45 minutes of the start of mixing.

CAUTION

- TARGET Cement/Silica Fume Slurry Grout contains Portland cement. Follow all of the safety precautions applicable to Portland cement and concrete when working with this product. See product label and SDS for details.
- Surface and ambient temperatures during the application and initial curing of TARGET Cement/Silica Fume Slurry Grout must be within the limits given in CSA A23.1, Section 23.4.

PACKAGING

TARGET Cement/Silica Fume Slurry Grout is supplied in 30 kg (66 lb) paper bags.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
® Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2025 Quikrete International, Inc.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

