FLOWCRETE

June, 2025 Page 1 of 3

PRODUCT

TARGET[®] Flowcrete consists of accurately weighed Portland cement, aggregates, and chemical admixtures. The product is designed to be used as original or repair concrete in situations requiring a high-quality concrete with a maximum aggregate size of 10 mm (3/8 inch). It may be mixed to any consistency from stiff plastic to flowable. An air-entraining agent is incorporated in the dry product to produce a concrete having good resistance to freezing and thawing. Shrinkage compensating agents are included to minimize plastic shrinkage. In areas requiring concrete exposed to chlorides, sulphates, or other severe environments, utilize TARGET Flowcrete with Silica Fume; a C-XL Exposure Class Concrete (CSA 23.1).



TYPICAL PROPERTIES OF TARGET FLOWCRETE

MIX CONSISTENCY	FLOWABLE	PLASTIC	STIFF PLASTIC
WATER ADDED Litres/25 kg bag (US quarts) / 55 lb bag	2.5 to 2.75 (2-3/5 to 3)	2.2 to 2.4 (2-1/3 to 2-1/2)	2.2 (2-1/3)
SLUMP, mm (in) CSA A23.2-5C	255 (10)	125 (5)	25 (1)
FLOW, cm (in) DIN EN 12350-5	60 (23.6)	40 (15.7)	30 (11.8)
AIR CONTENT, % volume [*] CSA A23.2-4C	6.2	5.8	4.6
VOLUME CHANGE % expansion Prior to initial set, unrestrained, CSA A23.2-1B After final set, CRD-C621 at 3 days at 7 days at 28 days ASTM C157 (modified) at 28 days, %	0 0.02 0.02 0.02 +0.008	Trace 0.01 0.01 0.01 0.01	0.6 0.01 0.01 0.01
COMPRESSIVE STRENGTH MPa (lb/in ²) CSA A23.2-3C,9C 100 mm diameter cylinders at 1 day at 3 days at 7 days at 28 days	13 (1900) 25 (3600) 34 (4900) 40 (5800)	20 (2900) 35 (5100) 44 (6400) 50 (7300)	23 (3300) 42 (6100) 52 (7500) 60 (8700)

The exact air content will vary, depending on the consistency of the mix and mixing procedures adopted. The values given are typical for rotating drum mixers.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA. (a) Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. (c) 2025 Quikrete International, Inc.



FLOWCRETE

June, 2025 Page 2 of 3

USES

TARGET Flowcrete is designed for uses such as the following:

- Grouting of keyways or general grouting operations where a maximum aggregate size of 10 mm (3/8 inch) is desirable.
- Levelling beds with a thickness of 25 mm (1 inch) or more.
- Void filling where a 10 mm (3/8 inch) aggregate is desirable or where the minimum dimension of the pour exceeds 25 mm (1 inch). For smaller dimensions, use TARGET Machine Base Grout, TARGET Portland Expanding Grout or TARGET 1118 Grout.
- Structural repairs and applications requiring a high quality concrete at any consistency between stiff plastic and flowable where the quantities involved or placement conditions make the use of conventional ready-mixed concrete impractical.

PROCEDURES

1. Prepare existing concrete surfaces for application of TARGET Flowcrete by thoroughly cleaning, using appropriate techniques to remove dirt, oil, laitance, efflorescence or deteriorated concrete.

Note: In some cases, such as overlays, levelling beds or repair work, a bonding slurry of TARGET Fast Set Patching Concrete with a mixture of one part by volume of TARGET Polymer Bonding Agent to two parts by volume of clean water is required. See product literature for TARGET Polymer Bonding Agent for additional details. Placing of TARGET Flowcrete over the slurry coat should be completed before the slurry dries and within one hour of mixing the slurry.

- 2. Add clean water to a suitable mixing container. Appropriate mixers include Jiffler or paddle mixers powered by a 1/2 inch drill, or high speed mortar mixers where batch sizes warrant the use of a larger mixer.
- 3. Add TARGET Flowcrete to water with continuous mixing to achieve the required consistency.
- 4. Mix for not less than 2 minutes. If material sits for more than 5 minutes, remix before placing.
- 5. Place and consolidate within 30 minutes of mixing, using methods suited to the application and consistency required.
- 6. Use conventional concrete finishing procedures to obtain the required surface finish. The use of magnesium or Plexiglass trowels has been found to give improved finishes to flatwork.
- Place only at ambient temperatures above 5 °C (40 °F) and below 30 °C (86 °F). Protect from freezing and from temperatures above 35 °C (95 °F) during the first three days after placing.



FLOWCRETE

June, 2025 Page 3 of 3

CAUTION

TARGET Flowcrete is a cement-rich material and while it is formulated for minimum plastic shrinkage it should be used with caution in large exposed areas in excess of 10 ft³. Adequate moist curing for at least 3 days from the time of placing is essential to reduce the potential for drying shrinkage cracking.

APPROXIMATE YIELD

CONSISTENCY	FLOWING	PLASTIC	STIFF PLASTIC
bags/m ³	80	82	84
bags/yd ³	61	63	65
ft ³ /bag	0.44	0.43	0.42

Based on 25 kg (55 lb) bag.

CHARACTERISTICS

COLOUR -	Uniform Gray
SHELF LIFE -	1 (one) year from date of manufacture when stored in a dry, protected and heated environment. (Production date and batching number stamped on side of each bag.)
HEALTH AND SAFETY -	Please consult Target Products Ltd. Safety Data Sheets for personal exposure risks and safe handling procedures.

PACKAGING

TARGET Flowcrete is available in 25 kg (55 lb) bag 56 bags/pallet or in 1 yd³, 1588 kg (3500 lb) bulk bags or 1134 kg (2500 lb) bulk bags 1/pallet.

T A R G E

Т

Ρ

R

O D U C T S