

MACHINE BASE GROUT

June, 2019 Page 1 of 5

PRODUCT

TARGET® Machine Base Grout is a premium quality non-metallic, non-shrink grout designed for use under severe service conditions. The grout consists of a precisely proportioned blend of Portland cement, stable natural aggregates, supplementary cementing materials including silica fume, expansion agents and special water reducing admixtures. The expansion agents are designed to give shrinkage compensation in both the plastic and hardened states, and include a crystal growth material to compensate for drying shrinkage. The grout is formulated to reduce the amount of mixing water required to give flowable mixes. The grout can be placed at dry-pack, plastic, flowable or fluid consistencies as defined in ASTM Standard C1107.



USES

TARGET Machine Base Grout is suitable for a wide range of cementitious grouting operations - from the most demanding non-shrink precision grouting to routine work. Typical grouting applications include:

- Pulp and paper machine sole plates.
- Under heavy machinery which transmits high stress to the grout, including milling machines and printing presses.
- Base plates of equipment or bridge bearing pads with dynamic loading.
- Column base plates.
- General machine base grouting.
- General grouting where the grout can be exposed to mild or moderate concentrations of many industrial chemicals. If required, the grout can be supplied with Sulphate-Resistant Cement.
- Most situations where a fluid, sanded grout is needed.
- Any situation where protection of embedded steel against corrosion is required.
- Patching or filling blockouts, and general concrete repairs.
- Installing anchor bolts or tie rods.

ADVANTAGES

The major advantages of TARGET Machine Base Grout include:

- Can be used at any consistency from dry-pack to flowable.
- Contains no metallic aggregates, making it suitable for service under wet or wet/dry conditions.
- Suitable for voids with least dimensions as small as 6 mm (0.25 in).
- Surface temperatures from below freezing to 50 °C (122 °F) are acceptable after curing as directed.
- Confinement is not essential - may be placed with exposed surfaces.
- Conforms to ASTM C1107 Type C expansion, both before and after initial set.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.

MACHINE BASE GROUT

June, 2019 Page 2 of 5

PROCEDURES

SURFACE PREPARATION

1. Remove all laitance, loose material, grease, oil and other contaminants from surfaces that will be in contact with the grout. Water blast or sandblast if necessary.
2. Saturate the host substrate with clean water prior to grouting. Just before grouting, remove all excess water and allow the substrate to become Saturated Surface-Dry or surface-damp when the grout is placed.

MIXING

WEAR IMPERVIOUS GLOVES, such as nitrile.

- **ALL CASES:**
Always add dry grout to clean water and mix to a uniform consistency, scraping the sides of the container as necessary. Mix continuously for a minimum of 3 minutes before use and continue mixing during placement. Use the grout within 30 minutes of the start of mixing. The temperature of the mixed grout should be 10 °C to 25 °C (50 °F to 77 °F).
- **FOR FLUID CONSISTENCY:**
To ensure adequate mixing of the grout use a high shear mixer such as a Jiffler mixer. Use not more than maximum 4.75 L (5 US qt) (of water per 25 kg (55 lb) bag of grout to produce a fluid mix. The actual amount of water required will vary with the temperature of the mix. If stiffening of the mix occurs, retempering with clean water within 20 minutes of the start of mixing is acceptable provided the recommended total water content is not exceeded.
- **FOR PLASTIC OR DRY PACK CONSISTENCY:**
Use a mortar mixer or equivalent and reduce the water content of the mix to achieve the required consistency. The first part of each batch should be mixed to a flowable consistency, then dry grout and more water can be added as necessary until the specified consistency is obtained.

PLACING

- Ensure the surfaces that will be in contact with the grout have been prepared as detailed in "Surface Preparation" and that no free water is present.
- For flowable mixes use form work and header boxes in accordance with standard grouting practices to ensure that grout is able to fill the voids totally. Flowable mixes can be placed by gravity flow or by pumping.
- Always place grout from one side of a void to allow air to be expelled ahead of the grout. Where necessary provide vents so that air will not be trapped.
- Use straps or light tapping if necessary to assist the flow of grout into voids. Machine Base Grout will normally flow into most voids without assistance. **DO NOT** use insertion vibrators.
- For dry-pack mixes ensure the voids are totally filled and the grout is properly compacted.

NOTE: Consult your TARGET technical representative for guidance in difficult or complex grouting jobs.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.



T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

MACHINE BASE GROUT

CURING

- Maintain base plate, substrate and grout temperatures in the range 5 °C to 35 °C (41 °F to 95 °F) for at least 72 hours after grouting.
- Exposed grout surfaces should be kept moist for at least three days after grouting. Alternatively, the use of Curing Compounds meeting the requirements of ASTM C309 are permitted after 24 hours of moist curing in situations where the ambient temperature and grout temperature do not exceed 25 °C (77 °F).

CAUTION

- Ambient temperatures should be between 5 °C (41 °F) and 35 °C (95 °F). If grouting is to be carried out at cooler or warmer temperatures than stated, please contact your TARGET Representative for special procedures.
- Foundation and base plate temperatures should be kept above 5 °C (41 °F) and below 35 °C (95 °F) for at least 72 hours after grouting. Contact your TARGET Technical Representative for advice on procedures and products for grout installation under colder conditions.
- If the minimum dimension of the grout is 150 mm (6 in) or more, clean -13 mm (-1/2 in) pea gravel should be added to the mix at up to 30% by weight of the original grout weight or TARGET Flowcrete can be used.
- Contact your TARGET representative for specific job recommendations.

PACKAGING

TARGET Machine Base Grout is supplied in 25 kg (55 lb) bags. Target Machine Base Grout can also be packaged in Bulk Bags for larger projects and is available on request. Lead time may be required.

YIELD

At fluid consistency, yield and quantity estimating values (excluding wastage allowance) are:

0.014 m ³ /bag	72 bags/m ³
0.49 ft ³ /bag	55 bags/yd ³

These values are based on standard 25 kg (55 lb) bags.

CHARACTERISTICS

COLOUR- Uniform Gray

SHELF LIFE - 1 (one) year from date of manufacture when stored in a dry, protected and heated environment. (Production date and batching number stamped on side of each bag.)

HEALTH AND SAFETY

Please consult Target Products Ltd. Safety Data Sheets for personal exposure risks and safe handling procedures.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.



T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

MACHINE BASE GROUT

June, 2019 Page 4 of 5

TYPICAL PROPERTIES OF TARGET MACHINE BASE GROUT

PHYSICAL PROPERTY	TEST METHOD		MIX CONSISTENCY			
	Canada	USA	Fluid *	Flowable	Plastic	Dry Pack
WATER DEMAND						
kg/kg	-	-	0.19	0.17	0.155	0.12
Liters/25 kg bag	-	-	4.75	4.25	3.87	3.00
US qt/55 lb bag	-	-	5	4-1/2	4	3-3/16
FLUIDITY , sec	CSA-A23.2-1B	ASTM C939	20-50	-	-	
Flow, %		ASTM C827		131	106	Forms a ball
BOND STRENGTH TO CONCRETE		ASTM C 1583		4.3 Mpa (624 PSI) (@ 28 Days)		
EXPANSION , % Volume	CSA-A23.2-1B	ASTM C940	1.2	1.0	1.2	N/A
After Final Set	-	ASTM C1090				
at 3 days		CRD-C621	0.07	0.03	0.03	
at 14 days			0.07	0.04	0.03	N/A
at 28 days			0.09	0.07	0.06	
BLEEDING , % Volume	CSA-A23.2-1B	ASTM C940	None	None	None	None
COMPRESSIVE STRENGTH , MPa (psi)	CSA-A23.2-1B	ASTM C109 ASTM C942				
at 24 hrs			18.6 (2700)	20.6 (2990)	24.5 (3550)	34.5 (5000)
at 3 days			35.2 (5100)	38.8 (5630)	41.5 (6020)	64.3 (9320)
at 7 days			50.4 (7310)	55.2 (8000)	59.2 (8580)	74.4 (10768)
at 28 days			64.5 (9350)	74.5 (10800)	80 (11603)	98.4 (14270)
Resistivity (HAS 1S-05-01)			7 day (ohm-cm)	5,150		
			28 day (ohm-cm)	16,410		
Rapid Chloride Permeability		ASTM C1202 AASHTO T277	Result	481 Coulombs (ASTM Rating - Very Low) (4" Thick sample @28 days)		
POROSITY , Boiled Absorption		ASTM C642				7.8 %
Permeable voids						15.2 %
Unit Mass/ Density (SSD) kg/M3 (P/cf)						2089 (131.2)
Chlorides (Water Soluble)	ASTM C114-19				Result	0.010%
Chlorides (Acid Soluble)	ASTM C114-19				Result	0.012%
Set Times (Cold Temp)	CAN3/CSA A5-M90	ASTM C266		Initial Set	19:30 @ 4°C	7:25 @ 23°C
				Final Set	28:10 @ 4°C	9:25 @ 23°C



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D

MACHINE BASE GROUT

June, 2019 Page 5 of 5

NOTES ON TYPICAL PROPERTIES:

- * Flow cone tests for mix consistency in accordance with ASTM C939 do not adequately describe the flow characteristics of thixotropic grouts such as TARGET Machine Base Grout compared to normal Hydraulic Portland Cement grouts. Flowable TARGET Machine Base Grout would be of equivalent consistency to a fluid Hydraulic Portland Cement Grout.
- * Stated values are as a result of testing conducted as per ASTM Standard Test Methods and Procedures in a 20 °C (68 °F) Laboratory environment.

T
A
R
G
E
T

P
R
O
D
U
C
T
S

L
T
D



NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
© Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.