

SACKING MIX

June, 2019 Page 1 of 1

PRODUCT

TARGET® Sacking Mix consists of accurately weighed Portland cement, fine aggregate and admixtures. The product is designed to develop high bond strength when applied to cast concrete surfaces. It is normally used at a flowable consistency. In normal working temperature ranges 10 °C to 24 °C (50 °F to 70 °F) the mix will have a slight expansion prior to final set. TARGET Sacking Mix contains no chloride admixtures.

COLOR

TARGET Sacking Mix has been formulated to approximate the color of typical Type 10 Portland cement concrete. The actual color achieved will, however, depend on the amount of water used in the mix and finishing techniques adopted.

USES

TARGET Sacking Mix is used to obtain architecturally acceptable finishes in cast concrete surfaces. It is used to patch and fill minor defects such as bugholes, honeycomb and segregation to provide a finish of uniform appearance. It is designed for application to exposed concrete surfaces such as columns, beams, walls, etc where uniformity of color and appearance are important.

PROCEDURES

1. The concrete surfaces to be finished should be thoroughly cleaned, then saturated with water and maintained wet for at least one hour before finishing operations begin. All free water on the surface should be removed prior to application of the TARGET Sacking Mix.
2. The flowable TARGET Sacking Mix mortar should be rubbed thoroughly over sections of the prepared concrete surfaces with clean burlap pads, or other approved methods, so that all the surface voids are filled.
3. While the applied mortar is still plastic (fresh), the surfaces should be rubbed with burlap pads using dry TARGET Sacking Mix. The final rubbing should be performed in such a manner that the filled voids are left flush with the surface of the surrounding concrete.
4. The finished surface should be adequately cured, commencing immediately after the Sacking Mix has set. Continuous moist curing for a minimum of 24 hours by water spray, damp sand or wet burlap is strongly recommended. If membrane curing compounds are used, be sure they do not interfere with the final appearance of the finished concrete surface.

YIELD

Each bag of TARGET Sacking Mix will cover approximately 15.3 to 20.5 m² (165 to 220 ft²) when mixed and applied as directed.

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.targetproducts.com/product-warranty
Or send a written request to Target Products Ltd., Five Concourse Parkway, Atlanta, GA 30328, USA.
® Quikrete Canada Holdings, Limited. Manufactured by Target Products Ltd. ©2019 Quikrete International, Inc.

